


# EJOT Super-SAPHIR® Self-Drilling COLORFAST JT3-D6H Range




## Ultimate Fastener Tensile Strength



Fastener Dia	kN
5.5/6.3 x L	11.50†


## Ultimate Fastener Shear Strength



Fastener Dia	kN
5.5/6.3 x L	7.50†

† Ultimate value of low thread shown

## Ultimate Pullout Load kN




Fastener Dia	Nominal Steel Thickness (mm)								Timber
	1.2	1.50	2.00	2.50	3.00	4.00	5.00	6.00	40mm Emb
5.5/6.3 x L	2.2	2.38	3.65	4.28	5.71	8.59	11.50*	11.50*	3.41

\* Pullout in 5 - 6mm steel is limited by the tensile strength of the fastener

Figures based on tests from steel up to 3.0mm thick designated as Grade Z35 (BS 2989), minimum yield strength 350 Nmm<sup>-2</sup>. Steel 4.0mm and thicker designated as grade S275 (BS EN 10025), minimum yield strength 275 Nmm<sup>-2</sup>.

## Ultimate Pullover Load kN



Washer Face	Nominal Sheet Thickness (mm)		
	0.50	0.70	0.90
CF15 Head	5.10	5.75	6.00
CF19 Head	5.50	6.20	6.50

Figures based on use with R38 profile steel sheets with fastener located in valley of profile and tested in accordance with BS 5427

Figures above are based on results obtained from tests carried out in our Applitec lab in accordance with equipment conforming to BS 5427 on a random sample of fasteners manufactured to EJOT tolerances. Information supplied should form part of a general guide and should performance data for a specific application be required please do not hesitate to contact us.

EJOT UK Limited Sherburn-in-Elmet, Leeds LS25 6PB.  
Tel: 01977 687040 Fax: 01977 687041  
www.ejot.co.uk info@ejot.co.uk

## Material Specification

### Head.

High impact coloured Nylon head, resistant to temperature from -40°C to 120°C, combined with UV stabilisers to ensure maximum colour retention in outdoor use. Incorporating an EPDM bonded sealing washer.

### Fastener

High quality Stainless steel grade 304 St/St, ISO group A2, Din Werkstoff 1.4301.

### Drill Point

High quality grade casehardened carbon steel to Din standard 10666.

